

**TYPE** 

#### **CONVEYOR AND PROCESS BELTS**

#### **TECHNICAL DATA SHEET**

# 2T12 U0-G25 HS GP

#### NA1136 CODE COMPOSITION Material Synthetic elastomer Thickness 2.50 mm 0.098 in. Surface GP pattern Colour Green Coefficient HF of friction Material Polyester (PET) **Textile** carcass Plies no. 2 Weft type Flexible Material Fabric with polyurethane (TPU) impregnation Thickness Surface pattern Fabric

TECHNICAL SPECIFICATIONS							
Total thickness		5.50 mm	0.22	in.			
Weight		4.50 kg/m <sup>2</sup>	0.92	lbs./sq.ft			
Elongation at 1%		12 N/mm	69.0	lbs./in.			
Max. admissible pull		24 N/mm	137.0	lbs./in.			
Temperature resistance (1)	min.	-40 °C	-40	°F			
resistance (1)	max.	100 °C	212	°F			
(1) use of the belt with limit values may reduce its life							
Minimum roller diame	eter <sup>(2)</sup>						
Knife edge		no					
<ul><li>Bending roller</li></ul>		80 mm	3.2	in.			
■ Counter-bending ro	100 mm	3.9	in.				
(2) The above mentioned values depend on the type of CHIORINO joint recommended							
Coefficient of friction on driving surface							
Raw steel sheet 0.		).20 [-]					
■ Laminated plastic/	).25 [-]						
Steel roller	.20 [-]						

0.30 [-]

1800 mm

# **SUITABLE FOR**

Max. production width

Rubberized roller


Colour

Grey

Corrugated carton: feeder

Packaging Airports

Cement industry



FEATURES	
Humidity influence	no
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	yes
Swan neck conveying	no
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	yes
Chemical resistances <u>link</u>	6

# **COMPLIANCES**

REACH EC 1907/2006 Regulation and Amendments

**NOTES** 

Issue: 10-10-2011 Last Update: 24-10-2019

71 in.

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



#### **CONVEYOR AND PROCESS BELTS**

### JOINING DATA SHEET

2T12 U0-G25 HS GP NA1136 CODE **TYPE** 

SKIVED JOINT '4' · Recommended joining procedure



Check our general catalogue to get further info on CHIORINO joining methods.

#### · Skiving instructions

Skiver			Straight/ Cam/	Pulley			Top cover					
			diagonal cut	wedge number	Т	В	Thickness adjustment	working	Т	В	Thickness adjustment	End stop switch of working
	mm	mm			mm	mm		plate	mm	mm		plate
B600 A	5,5	65	Diagonal	1.5-10		0	18,35	110		15	14,6	120
B300 SA												

#### · Guide to the use of adhesives

Pour the I hardener with the R cement (pot-life 2 hours).

Apply a thin layer of above mix on both splices.


Let dry for 5 minutes, then match the belt ends, paying attention to align properly.

Press according to the instructions shown.

To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

Kit: SINTECOL

## · Layout of components



Press settings					
Upper platen temperature	100 °C				
Lower platen temperature	100 °C				
Curing time in press	25 min.				
Driving torque	30				

Cooling time: it is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.

### Notes

Issue: 18-06-2011 Last Update: 30-01-2014

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.